

PROPOSED DRAFT
NOVEMBER 2014

409.03.3 Seal Coat Limitations

The following conditions govern seal coat work:

7. Do not apply bituminous material within 72 hours of performing crack sealing.

COMMENTS:

1. The addition of (7) "Do not apply bituminous material within 72 hours of performing crack sealing" is unworkable unless MDT intends to add three days of contract time when this spec is implemented. Charging three days of contract time when the contractor cannot chip seal is simply untenable and must be addressed.

Response: The Department takes specifications into account when setting up contract time. If no other work is being performed (which is typically the case with this type of work), time will not be charged.

FINAL DRAFT
EFFECTIVE FEBRUARY 26, 2015

409.03.3 Seal Coat Limitations

The following conditions govern seal coat work:

7. Do not apply bituminous material within 72 hours of performing crack sealing.