

PROPOSED DRAFT MAY 2015

407.03.3 Application of Emulsified Materials

Dilute emulsified asphalt to a 50-50 ratio with water, unless other approved proportions are directed by the Project Manager. Ensure dilution occurs prior to the emulsified material leaving the supplier. Apply diluted emulsified asphalt for tack coat as specified by the Project Manager at a minimum rate of 0.1 gallon per square yard (0.45 L/m²).

When a double shot of emulsion is called for in the contract, apply 2 applications at the minimum rate specified above. Ensure the first shot is cured prior to applying the second.

COMMENTS

1. Regarding the proposed change to 407.03.3 At this point implementing a requirement for all dilution to occur at the point of manufacture for tack is probably a little premature. We need to weigh the pros and cons and little more.

DROPPED